

ABSTRACT

5 A polyamide resin/rubber-reinforced styrene-based  
resin composition, particularly, a polyamide resin/ABS  
resin composition, excellent in the balance between  
impact strength and fluidity as well as in the heat  
resistance, chemical resistance and paintability, as well  
as a shaped article thereof, are provided. The resin  
composition comprises 100 parts by weight of a  
10 thermoplastic resin comprising (A) from 79.5 to 20 parts  
by weight of a polyamide resin, (B) from 20 to 79.5 parts  
by weight of a polymer obtained by grafting an aromatic  
vinyl-based monomer and a vinyl cyanide-based monomer to  
a specific rubber-like polymer, (C) from 0.5 to 60 parts  
15 by weight of an unsaturated carboxylic acid-modified  
copolymer obtained by copolymerizing an unsaturated  
carboxylic acid, an aromatic vinyl-based monomer and a  
vinyl cyanide-based monomer, and (D) from 0 to 50 parts  
by weight of a copolymer obtained by copolymerizing an  
20 aromatic vinyl-based monomer and a vinyl cyanide-based  
monomer (with the proviso that the total of (A), (B), (C)  
and (D) is 100 parts by weight), and if desired, further  
comprises (E) from 0.05 to 150 parts by weight of an  
inorganic filler.